


Acrylic acid ester, for manufacturing polymers and for use as a feed stock for syntheses



CAS # 7328-17-8

EINECS # 230-811-7

MOLECULAR FORMULAC₉H₁₆O₄**MOLAR MASS**

188.3 g/mol

PRODUCT SPECIFICATION

Properties	Typical	Method
Ester content	min 90.0 %	Gas chromatography
Water content	max 0.1 %	ASTM E 203
Acid content (calc. as acrylic acid)	max 0.1 %	ASTM D 1613
Color on dispatch	max. 150	APHA, ASTM D 1209
Standard stabilization	1000 ± 200 ppm MEHQ 1000 ± 200 ppm BHT	ASTM D 3125

The aforementioned data shall constitute the agreed contractual quality of the product at the time of passing of risk. The data are controlled at regular intervals as part of our quality assurance program. Neither these data nor the properties of product specimens shall imply any legally binding guarantee of certain properties or of fitness for a specific purpose. No liability of ours can be derived therefrom.

OTHER PROPERTIES

Properties	Typical	Method
Appearance	Clear, colorless	
Physical form	Liquid	
Odor	Ester-like	
Density @ 25 °C	1.0028 g/cm ³	
Refractive index n _d @ 20 °C	1.438	
Boiling point @ 5 hPa	95 °C	
Freezing point	-61.9 °C	
Viscosity @ 25 °C	approx. 5 mPa · s	
Vapor pressure @ 38.9 °C	0.153 mbar	

Jamorin has Material Safety Data Sheets (MSDS) for each products. The MSDS contain relevant information needed to safeguard your employees from any known safety and health hazard related with our products. Jamorin provides you MSDS for all the products you evaluate or buy. It is also necessary that you get copies of the MSDS of the other raw materials recommended in our technical bulletins from the suppliers. Your employees should have ready access to and to be trained well on the proper use of MSDS

APPLICATIONS

Ethyldiglycol Acrylate (EDGA) forms homopolymers and copolymers. Copolymers of Ethyldiglycol Acrylate (EDGA) can be prepared with acrylic acid and its salts, amides and esters, and with methacrylates, acrylonitrile, maleic acid esters, vinyl acetate, vinyl chloride, vinylidene chloride, styrene, butadiene, unsaturated polyesters and drying oils, etc. Ethyldiglycol Acrylate (EDGA) is also a very useful feedstock for chemical syntheses, because it readily undergoes addition reactions with a wide variety of organic and inorganic compounds.

FEATURES AND BENEFITS

Ethyldiglycol Acrylate (EDGA) can be used to impart the following properties to polymers:

- Adhesion
- Low VOC

STORAGE & HANDLING

In order to prevent polymerization, Ethyldiglycol Acrylate (EDGA) must always be stored under air, and never under inert gases. The presence of oxygen is required for the stabilizer to function effectively. It has to contain a stabilizer and the storage temperature must not exceed 35 °C. Under these conditions, a storage stability of one year can be expected upon delivery. In order to minimize the likelihood of overstorage, the storage procedure should strictly follow the «first-in-first-out» principle. For extended storage periods over 4 weeks it is advisable to replenish the dissolved oxygen content.

Storage tanks and pipes should be made of stainless steel or aluminum. Storage tanks, pumps and pipes should be earthed.

SAFETY

A Safety Data Sheet has been compiled for Dihydrodipentadienyl Acrylate (DCPA) that contains up-to-date information on questions relevant to safety.

PACKAGING

A Safety Data Sheet has been compiled for Ethyldiglycol Acrylate (EDGA) that contains up-to-date information on questions relevant to safety.

NOTE

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

DISCLAIMER «It is in good faith that we offer suggestions on the use of our products and these are based on knowledge we believe are correct and dependable. However, these are with no guarantee as process and conditions in the use of our products may vary and are beyond our control. We strongly recommend that users of our products verify the appropriateness of our suggestions before using them on a commercial scale».

COPYRIGHT PROTECTION STATEMENT 2020, All right reserved

